



P. O. Drawer E  
 Garyville, LA 70051  
 Tel: (985) 535-2000  
 Fax: (985) 535-1234

## 1350N

### 55 MELT FLOW HOMOPOLYMER POLYPROPYLENE FOR INJECTION MOLDING

#### Product Description and Applications:

Pinnacle Polymers Polypropylene 1350N is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for general-purpose injection molding of thin wall containers. 1350N contains a nucleation additive package.

#### Features:

The 1350N product provides:

- Superior color and processing stability
- Good flow characteristics
- Low odor and taste
- High melt flow

Pinnacle's polypropylene, as marketed by Pinnacle Polymers, in natural, uncolored pellet form complies with appropriate requirements of CFR Title 21, Part 177, Subpart B, Section 177.1520 (c) 1.1a entitled "Olefin Polymers" of the Food Additives Amendment of 1958 to the United States Food, Drug and Cosmetic Act of 1938.

### Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	55 g/10 min.	55 g/10 min.	D1238 <sup>1</sup>
Density at 23°C	0.9 g/cm <sup>3</sup>	900 kg/m <sup>3</sup>	D1505
Tensile yield strength, at 51 mm/min	5800 psi	40 MPa	D638 <sup>2</sup>
Yield elongation, at 51 mm/min	8%	8%	D638 <sup>2</sup>
Flexural modulus (1% secant) at 1.27 mm/min	290,000 psi	2000 MPa	D790A <sup>2</sup>
Notched Izod impact strength, at 73°F/23°C	0.5 ft-lb/in	27 J/m	D256 <sup>2</sup>

<sup>1</sup>Condition L 230/2.16

<sup>2</sup>ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

UNIPOL is a trademark of Union Carbide Corporation