



P. O. Drawer E
 Garyville, LA 70051
 Tel: (985) 535-2000
 Fax: (985) 535-1234

3208

8 MELT FLOW HIGH IMPACT COPOLYMER FOR INJECTION MOLDING

Product Description and Applications:

Pinnacle Polymers Polypropylene 3208 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for injection molding of automotive and consumer product applications. Also contains a long-term heat aging additive system.

Features:

The 3208 product provides:

- Wet/Dry environment resistance
- Superior balance of stiffness and impact strength
- Excellent long term heat aging properties
- Excellent color and processing stability
- Enhanced weld-line strength

Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	8 g/10 min.	8 g/10 min.	D1238 ¹
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Tensile yield strength, at 51 mm/min	3500 psi	24.1 MPa	D638 ²
Yield elongation, at 51 mm/min	7%	7%	D638 ²
Flexural modulus (1% secant) at 1.27 mm/min	160,000 psi	1103 MPa	D790A ²
Notched Izod impact strength, at 73°F/23°C	≥ 6 ft-lb/in	≥ 320 J/m	D256 ²
Gardner Impact strength at -22°F/-30°C	300 in-lb	33 J	D5420 ³

¹Condition L 230/2.16

²ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

³Method G, Geometry GC

UNIPOL is a trademark of Union Carbide Corporation